

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
21 February 2002 (21.02.2002)

PCT

(10) International Publication Number  
**WO 02/13767 A2**

- (51) International Patent Classification<sup>7</sup>: **A61K 6/083**
- (21) International Application Number: PCT/US01/25031
- (22) International Filing Date: 9 August 2001 (09.08.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
60/224,669 11 August 2000 (11.08.2000) US
- (71) Applicant: **DENTSPLY INTERNATIONAL INC.**  
[US/US]; 570 West College Avenue, P.O. Box 872, York,  
PA 17405-0872 (US).
- (72) Inventors: **WALZ, Uwe**; Zum Klausenhorn 9, 78465 Kon-  
stanz (DE). **KLEE, Joachim, E.**; 78315 Radolfzell (DE).
- (74) Agents: **HURA, Douglas, J.** et al.; Dentsply International  
Inc., 570 West College Avenue, P.O. Box 872, York, PA  
17404-0872 (US).
- (81) Designated States (*national*): CA, JP.
- (84) Designated States (*regional*): European patent (AT, BE,  
CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,  
NL, PT, SE, TR).
- Published:**  
— *without international search report and to be republished  
upon receipt of that report*
- For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.*



**WO 02/13767 A2**

(54) Title: POLYAMINOESTER AND THEIR APPLICATION IN DENTAL COMPOSITIONS

(57) Abstract: Dental compositions comprising at least a polymerizable monomer and/or at least a polyaminoester that are prepared by reaction of bis- or polyacrylic esters and amines, pigments, organic and/or inorganic fillers, initiators and stabilizers.

## ***Polyaminoester and their application in dental compositions***

5



### ***Technical background***


Since some years, the addition polymerization of bisacrylamides and amines is well-known (P. Ferrutti et al., Polymer **26** (1985) 1336). Bisacrylamides are much more stable against hydrolysis compared to acrylic esters. The reaction of amines and esters lead to an transamidation reaction (H.-G. Elias, Makromoleküle, Hüttig&Wepf, Basel, 1990, p.555). Consequently, the assumption was that a reaction of acrylic esters and amines should lead to an cleavage of ester bonds. Therefore, the formation of addition polymers, prepolymers and macromonomers of amines and acrylic esters should be impossible.

Recently, oligoamido amines and oligoester amines based on antibiotics containing .beta.-lactam rings were investigated (Panayotov, Eur. Polym. J. **32** (1996) 957-962). They were prepared by interaction between ampicillin and amoxicillin and methylenebisacrylamide, 1,4-diacryloylpiperazine and 1,3-propanediol diacrylate.


### ***Description of the invention***

Dental compositions comprising at least a polymerizable monomer and/or at least a polyaminoester of formulas **1** to **6**, pigments, organic and/or inorganic fillers, initiators and stabilizers.


**1****2**




3



4



5



6

5 wherein


R<sub>1</sub> denotes is a difunctional substituted or unsubstituted C<sub>1</sub> to C<sub>18</sub> alkylene, difunctional substituted or unsubstituted cycloalkylene, difunctional substituted or unsubstituted C<sub>5</sub> to C<sub>18</sub> arylene or heteroarylene, difunctional substituted or unsubstituted C<sub>5</sub> to C<sub>18</sub> alkylarylene or alkylheteroarylene, difunctional substituted or unsubstituted C<sub>7</sub> to C<sub>30</sub> alkylene arylene,

R<sub>2</sub> denotes is a difunctional substituted or unsubstituted C<sub>1</sub> to C<sub>18</sub> alkylene, difunctional substituted or unsubstituted cycloalkylene, difunctional substituted or unsubstituted C<sub>5</sub> to C<sub>18</sub> arylene or heteroarylene, difunctional substituted or unsubstituted C<sub>5</sub> to C<sub>18</sub> alkylarylene or alkylheteroarylene, difunctional substituted or unsubstituted C<sub>7</sub> to C<sub>30</sub> alkylene arylene.


R<sub>3</sub> denotes H or a substituted or unsubstituted C<sub>1</sub> to C<sub>18</sub> alkylene, substituted or unsubstituted cycloalkylene, substituted or unsubstituted C<sub>5</sub> to C<sub>18</sub> arylene or heteroarylene, substituted or unsubstituted C<sub>5</sub> to C<sub>18</sub> alkylarylene or alkylheteroarylene, substituted or unsubstituted C<sub>7</sub> to C<sub>30</sub> alkylene arylene,

$n$  is an integer.


Preferably the invented dental composition contains a polyaminoester that are characterized by the following formulas



7



8




9


wherein

- 5  $R_1$  denotes is a difunctional substituted or unsubstituted  $C_1$  to  $C_{18}$  alkylene, difunctional substituted or unsubstituted cycloalkylene, difunctional substituted or unsubstituted  $C_5$  to  $C_{18}$  arylene or heteroarylene, difunctional substituted or unsubstituted  $C_5$  to  $C_{18}$  alkylarylene or alkylheteroarylene, difunctional substituted or unsubstituted  $C_7$  to  $C_{30}$  alkylene arylene,
- 10  $R_2$  denotes is a difunctional substituted or unsubstituted  $C_1$  to  $C_{18}$  alkylene, difunctional substituted or unsubstituted cycloalkylene, difunctional substituted or unsubstituted  $C_5$  to  $C_{18}$  arylene or heteroarylene, difunctional substituted or unsubstituted  $C_5$  to  $C_{18}$  alkylarylene or alkylheteroarylene, difunctional substituted or unsubstituted  $C_7$  to  $C_{30}$  alkylene arylene, and
- 15  $n$  is an integer.

Most preferably polyaminoesters are applied characterized by the following formulas



10



20

11

wherein n is an integer.

Said polymerizable monomer preferably are hydroxyethyl methacrylate, hydroxyethylacrylate, hydroxypropyl methacrylate, ethyleneglykol dimethacrylate, diethyleneglykol dimethacrylate, triethyleneglykol dimethacrylate, 3,(4),8,(9)-Dimethacryloyl-(oxymethyl)-tricyclo-5.2.1.0<sup>2,6</sup> decane, trimethylolpropane triacrylate or trimethylolpropane trimethacrylate, N,N'-dimethylaminoethyl methacrylate.

As fillers are applied inorganic or organic, reactive or nonreactive, surface modified or nonmodified glasses such as polymer granulate or a combination of organic and/or inorganic fillers, strontium aluminosilicate glass, La<sub>2</sub>O<sub>3</sub>, BiPO<sub>4</sub>, ZrO<sub>2</sub>, BaWO<sub>4</sub>, CaWO<sub>4</sub>, SrF<sub>2</sub>, Bi<sub>2</sub>O<sub>3</sub>.

Instead of primary monoamine and dissecondary diamines the usage of polyamines is possible, too, leading to crosslinked polyaminoesters.

The invented dental composition preferably is applicable as root canal sealing material or as temporary crown & bridge material.

### Example 1

5.000 g (22.097 mmol) Hexamethyldiacrylate (Servo Delden) and 7.525 g (22.097 mmol) N,N'-Dibenzyl-5-nonandiamin-1,9 were mixed homogeneously and stirred at 60°C for 4 days. After that time a complete conversion was found indicated by disappearance of the double bonds at 1635 / 1619 cm<sup>-1</sup>.

Yield: 12.525 g (100 % of th.)

(C<sub>34</sub>H<sub>50</sub>N<sub>2</sub>O<sub>5</sub>)<sub>n</sub>, (566.8)<sub>n</sub>

[η] = 8.57 ml/g (Viscosity in THF solution)

IR: 2920 / 2865 (CH<sub>2</sub>), 1735 (CO)

M<sub>n</sub> (GPC) = 2225 (4661) g/mol

M<sub>w</sub> (GPC) = 9398 (10200) g/mol

### Example 2

20.000 g (88.39 mmol) Hexamethyldiacrylate (Servo Delden) and 15.719 g (106.07 mmol) 3,6-Dioxaoctan-diamin-1,8 (Fluka) were mixed homogeneously and stirred at room temperature for 1.5 hours. After that time

a complete conversion was found indicated by disappearance of the double bonds at 1635 / 1619  $\text{cm}^{-1}$ .

Yield: 35.719 g (100 % of th.)

$(\text{C}_{18}\text{H}_{34}\text{N}_2\text{O}_6)_n$ , (347.5)<sub>n</sub>

- 5  $\eta = 4.73 \pm 0.05 \text{ Pa}\cdot\text{s}$  (dynamic viscosity measured using Bohlin CS50 rheometer)

IR: 3325 (NH), 2920 / 2865 ( $\text{CH}_2$ ), 1735 (CO)

$^{13}\text{C}$ -NMR ( $\text{CDCl}_3$ ): 172.6/172.4 (6), 73.4 (2); 70.5/70.2 (3); 64.2 (7), 49.8 (1), 45.0 (4), 41.7 (4), 34.8 (5), 28.4 (8), 25.5 (9)

- 10 IR: 3325 (NH), 2920 / 2865 ( $\text{CH}_2$ ), 1735 (CO)

### Example 3

10.000 g (58.77 mmol) Ethylene glycol diacrylate and 14.125 g (58.77 mmol) N,N'-Dibenzylethylenediamine were mixed homogeneously and stirred  
15 at room temperature for 40 hours at 60°C. After that time a complete conversion was found indicated by disappearance of the double bonds at 1635 / 1619  $\text{cm}^{-1}$ .

Yield: 24.125 g (100 % of th.)

- 20  $\eta = 1557 \pm 17 \text{ Pa}\cdot\text{s}$  (dynamic viscosity measured using Bohlin CS50 rheometer)

$[\eta] = 9.176 \text{ ml/g}$  (viscosity in THF solution)


$M_n$  (GPC) = 1575 g/mol

$M_w$  (GPC) = 10060 g/mol

$(\text{C}_{24}\text{H}_{32}\text{N}_2\text{O}_4)_n$ , (410.5)<sub>n</sub>

- 25 IR: 3060 / 3028; 2953 / 2816 ( $\text{CH}_2$ ), 1743 (CO)

$^{13}\text{C}$  NMR ( $\text{CDCl}_3$ ): 49.7 (1), 32.4 (2), 172.6 (3), 621.0 (4), 51.5 (5), 58.6 (6), 139.2 (7), 128.6 (8), 128.0 (9), 126.8 (10)





temperature. After that time a complete conversion was found indicated by disappearance of the double bonds at 1635 / 1619  $\text{cm}^{-1}$ .

Yield: 15.710 g (100 % of th.)

$\eta$  = Pa\*s (dynamic viscosity measured using Bohlin CS50 rheometer)

5  $(\text{C}_{28}\text{H}_{42}\text{N}_2\text{O}_8)_n$ , (534.7)<sub>n</sub>

IR: 3445 / 3332 (NH), 2947 / 2875 / 2821( $\text{CH}_2$ ), 1729 (CO); 1637 / 1619 ( $\text{C}=\text{C}$ )

### Example 7

10 10.000 g (58.77 mmol) Ethylene glykol diacrylate and 22.840 5.710 g (117.54 mmol) 3,(4),8,(9)-Bis(aminomethyl)-tricyclo-5.2.1.0<sup>2,6</sup> decane were mixed homogeneously and stirred at room temperature for 2 hours at room temperature. After that time a complete conversion was found indicated by disappearance of the double bonds at 1635 / 1619  $\text{cm}^{-1}$ .


15 Yield: 32.840 g (100 % of th.)

$\eta$  = 218800  $\pm$  1990 Pa\*s (dynamic viscosity measured using Bohlin CS50 rheometer)

$(\text{C}_{32}\text{H}_{54}\text{N}_4\text{O}_4)_n$ , (558.8)<sub>n</sub>

IR: 3373 / 3286 (NH), 2960 / 2888 ( $\text{CH}_2$ ), 1743 / 1731 (CO)

20  $^{13}\text{C}$  NMR ( $\text{CDCl}_3$ ): 47.5 (1), 34.3/34.7 (2), 172.9 (3), 66.0 (4), 55.3 (5), signals of (6) to (15) between 24.5 and 63.5 ppm



### 25 Example 8

To 10.000 g (58.77 mmol) Ethylene glykol diacrylate dissolved in 50 ml THF were slowly added at 0 to 5°C under stirring a solution of 8.709 g (58.77 mmol) 3,6-Dioxaoctane diamine-1,8 in 50 ml THF. After adding the amine the solution was stirred at room temperature for 1.5 hours. After that time a complete conversion was found due to the disappearance of the double bonds at 1635 / 1619  $\text{cm}^{-1}$ . Then the solvent was removed and the addition polymer was dried in vacuum.

30



Yield: 18.709 g (100 % of th.)

$\eta$  = Pa\*s (dynamic viscosity measured using Bohlin CS50 rheometer)

$(C_{14}H_{26}N_2O_6)_n$ , (318.4)<sub>n</sub>

IR: 3373 / 3286 (NH), 2960 / 2888 (CH<sub>2</sub>), 1743 / 1731 (CO)

5

### **Application Example 1 (Dental root canal sealer)**

#### **Paste A**

8.404 g (37.14 mmol) Hexamethyldiacrylate (Servo Delden), 25.968  
10 g CaWO<sub>4</sub>, 6.492 g ZrO<sub>2</sub> and 0.325 g aerosil were mixed homogeneously.

#### **Paste B**

7.217 g (37.14 mmol) 3,(4),8,(9)-Bis(aminomethyl)-tricyclo-5.2.1.0<sup>2,6</sup>  
decane, 28.867 g CaWO<sub>4</sub>, 7.217 g ZrO<sub>2</sub> and 0.722 g aerosil were mixed  
15 homogeneously.

### **Dental root canal sealer**

Immediately before use 0.214 g of Paste A and 0.200 g of Paste B  
were mixed homogeneously. The setting time of the root canal sealing  
20 material is 30 minutes. The radiopacity of 12.8 mm/ mm Al.

### **Application Example 2 (Dental root canal sealer)**

#### **Paste A**

25 2.5213 g (11.14 mmol) Hexamethyldiacrylate (Servo Delden),  
12.9298 g CaWO<sub>4</sub>, 3.2325 g ZrO<sub>2</sub> and 0.0385 g aerosil were mixed  
homogeneously.


#### **Paste B**

30 0.801 g (5.29 mmol) 1-Aminoadamantane, 1.802 g (5.29 mmol) N,N'-  
Dibenzyl-5-oxanonandiamin-1,9, 0.103 g (0.53 mmol) 3,(4),8,(9)-  
Bis(aminomethyl)-tricyclo-5.2.1.0<sup>2,6</sup> decane, 10.411 g CaWO<sub>4</sub>, 2.603 g ZrO<sub>2</sub>  
and 0.315 g aerosil were mixed homogeneously.


**Dental root canal sealer**

Immediately before use 0.173 g of Paste A and 0.200 g of Paste B were mixed homogeneously. The setting time of the root canal sealing material is 30 minutes. The radiopacity of 13.8 mm/ mm Al.


1. Dental compositions comprising at least a polymerizable monomer and/or at least a polyaminoester of formulas **1** to **6**, pigments, organic and/or inorganic fillers, initiators and stabilizers.




**1**




**2**




**3**



**4**



**5**



**6**

wherein




$\text{R}_1$  denotes is a difunctional substituted or unsubstituted  $\text{C}_1$  to  $\text{C}_{18}$  alkylene, difunctional substituted or unsubstituted cycloalkylene, difunctional substituted or unsubstituted  $\text{C}_5$  to  $\text{C}_{18}$  arylene or heteroarylene, difunctional substituted or unsubstituted  $\text{C}_5$  to  $\text{C}_{18}$  alkylarylene or alkylheteroarylene, difunctional substituted or unsubstituted  $\text{C}_7$  to  $\text{C}_{30}$  alkylene arylene,

$R_2$  denotes is a difunctional substituted or unsubstituted  $C_1$  to  $C_{18}$  alkylene, difunctional substituted or unsubstituted cycloalkylene, difunctional substituted or unsubstituted  $C_5$  to  $C_{18}$  arylene or heteroarylene, difunctional substituted or unsubstituted  $C_5$  to  $C_{18}$  alkylarylene or alkylheteroarylene, 5 difunctional substituted or unsubstituted  $C_7$  to  $C_{30}$  alkylene arylene,

$R_3$  denotes H or a substituted or unsubstituted  $C_1$  to  $C_{18}$  alkylene, substituted or unsubstituted cycloalkylene, substituted or unsubstituted  $C_5$  to  $C_{18}$  arylene or heteroarylene, substituted or unsubstituted  $C_5$  to  $C_{18}$  alkylarylene or alkylheteroarylene, substituted or unsubstituted  $C_7$  to  $C_{30}$  10 alkylene arylene,

$n$  is an integer.

2. Dental composition of claim 1, wherein said polyaminoester is characterized by the following formulas




wherein

$R_1$  denotes is a difunctional substituted or unsubstituted  $C_1$  to  $C_{18}$  alkylene, 20 difunctional substituted or unsubstituted cycloalkylene, difunctional substituted or unsubstituted  $C_5$  to  $C_{18}$  arylene or heteroarylene, difunctional substituted or unsubstituted  $C_5$  to  $C_{18}$  alkylarylene or alkylheteroarylene, difunctional substituted or unsubstituted  $C_7$  to  $C_{30}$  alkylene arylene,

$R_2$  denotes is a difunctional substituted or unsubstituted  $C_1$  to  $C_{18}$  alkylene, 25 difunctional substituted or unsubstituted cycloalkylene, difunctional substituted or unsubstituted  $C_5$  to  $C_{18}$  arylene or heteroarylene, difunctional


substituted or unsubstituted C<sub>5</sub> to C<sub>18</sub> alkylarylene or alkylheteroarylene,  
difunctional substituted or unsubstituted C<sub>7</sub> to C<sub>30</sub> alkylene aryene, and  
n is an integer.

- 5     3. Dental composition of claim 1, wherein said polyaminoesters preferably is characterized by the following formula



wherein n is an integer.

- 10    4. Dental composition of claim 1, wherein said polyaminoesters preferably is characterized by the following formula



wherein n is an integer.

- 15    5. Dental composition of claim 1, wherein said polyaminoesters are composed of polyamines and bis- or polyacrylates.
6. Dental composition of claim 1, wherein said polyaminoesters are copolymerized with monomers that are usable for step-growth polymerization, preferably with di- or polyepoxides or di- or polyisocyanates.
- 20    7. Dental composition of claim 1, wherein said polymerizable monomer preferably is hydroxyethyl methacrylate, hydroxyethylacrylate, hydroxypropyl methacrylate, ethyleneglykol dimethacrylate, diethyleneglykol dimethacrylate, triethyleneglykol dimethacrylate, 3,(4),8,(9)-Dimethacryloyl-(oxymethyl)-tricyclo-5.2.1.0<sup>2,6</sup> decane, trimethylolpropane triacrylate or trimethylolpropane trimethacrylate, N,N'-dimethylaminoethyl methacrylate.
- 25

8. Dental composition of claim 1, wherein said fillers are functionalized or non-functionalized organic polymers or wherein said fillers are inorganic or organic, reactive or non-reactive, surface modified or non-modified glasses such as polymer granulate or a combination of organic and/or inorganic fillers, strontium aluminosilicate glass,  $\text{La}_2\text{O}_3$ ,  $\text{BiPO}_4$ ,  $\text{ZrO}_2$ ,  $\text{BaWO}_4$ ,  $\text{CaWO}_4$ ,  $\text{SrF}_2$ ,  $\text{Bi}_2\text{O}_3$ .
9. Dental composition of claim 1, applicable as root canal sealing material.
10. Dental composition of claim 1, applicable as temporary crown & bridge material.